

Customer No.: 31561  
Application No.: 10/709,990  
Docket No.: 11416-US-PA

### AMENDMENTS

#### IN THE CLAIMS:

Please amend the claims according to the following listing of claims and substitute it for all prior versions and listing of claims in the application.

1. (currently amended) A solder composition, comprising:  
chromium (Cr) in an amount of 5~20 wt.%;  
stibium (Sb) in an amount of 0.01~50 wt.%;  
a component selected from a the group consisting of tin (Sn), zinc (Zn), bismuth (Bi),  
indium (In) and a mixture thereof; and  
an impurity.
2. (currently amended) The solder composition according to claim 1, further comprising another component selected from a the IVB group in the periodic table or a mixture thereof in an amount of 0.01~10 wt.%.
3. (currently amended) The solder composition according to claim 1, further comprising another component selected from a the VB group in the periodic table or a mixture thereof in an amount of 0.01~10 wt.%.

Customer No.: 31561  
Application No.: 10/709,990  
Docket No.: 11416-US-PA

4. (currently amended) The solder composition according to claim 1, further comprising another component selected from ~~a~~ the IIIB group in the periodic table or a mixture thereof in an amount of 0.01~20 wt.%.

5. (original) The solder composition according to claim 4, wherein the component selected from the IIIB group in the periodic table or a mixture thereof at least comprises cerium (Ce), samarium (Sm), neodymium (Nd), lutetium (Lu) or a mixture thereof.

6. (original) The solder composition according to claim 1, further comprising another component selected from silver (Ag), copper (Cu) or a mixture thereof having an amount of 0.01~10 wt.%.

7. (cancelled).

8. (original) The solder composition according to claim 1, further comprising another component selected from nickel (Ni), cobalt (Co), manganese (Mn) or a mixture thereof in an amount of 0.01~5 wt.%.

9. (original) The solder composition according to claim 1, further comprising gallium (Ga) in an amount of 0.01~10 wt.%.

10. (currently amended) A solder composition, comprising:

Customer No.: 31561  
Application No.: 10/709,990  
Docket No.: 11416-US-PA

chromium (Cr) in an amount of 0.01~5 wt.%;

stibium (Sb) in an amount of 0.01~50 wt.%;

a component selected from ~~a~~the group consisting of tin (Sn), zinc (Zn), bismuth (Bi), indium (In) and a mixture thereof; and  
an impurity.

11. (original) The solder composition according to claim 10, further comprising another component selected from silver (Ag), copper (Cu) or a mixture thereof having an amount of 0.01~10 wt.%.

12. (cancelled).

13. (original) The solder composition according to claim 10, further comprising another component selected from nickel (Ni), cobalt (Co), manganese (Mn) or a mixture thereof in an amount of 0.01~5 wt.%.

14. (original) The solder composition according to claim 10, further comprising gallium (Ga) in an amount of 0.01~10 wt.%.